Yuyao PBT 4029G30

Polybutylene Terephthalate

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PBT 4029G30 is a Polybutylene Terephthalate (PBT) product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PBT 4029G30 include electrical/electronic applications, automotive and engineering/industrial parts. Characteristics include: Creep Resistant Fatigue Resistant Good Dimensional Stability Good Processability Heat Resistant

| General Information | | | | | |
|----------------------------|----------------------------|-------|-------------|--|--|
| Features | Electrically Insulating | | | | |
| | Fatigue Resistant | | | | |
| | Good Creep Resistance | | | | |
| | Good Dimensional Stability | | | | |
| | Good Impact Resistance | | | | |
| | Good Processability | | | | |
| | High Heat Resistance | | | | |
| Uses | Automotive Applications | | | | |
| | Automotive Under the Hood | | | | |
| | Connectors | | | | |
| | Electrical Parts | | | | |
| | Printed Circuit Boards | | | | |
| | Valves/Valve Parts | | | | |
| | | | | | |
| Appearance | Colors Available | | | | |
| Processing Method | Injection Molding | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Specific Gravity | 1.43 | g/cm³ | ASTM D792 | | |
| Molding Shrinkage - Flow | 1.5 to 2.0 | % | ASTM D955 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength | 62.0 | MPa | ASTM D638 | | |
| Tensile Elongation (Break) | 3.5 | % | ASTM D638 | | |
| Flexural Modulus | 2400 | MPa | ASTM D790 | | |
| Flexural Strength | 77.7 | MPa | ASTM D790 | | |
| Impact | Nominal Value | Unit | Test Method | | |
| Notched Izod Impact (Area) | 10.0 | kJ/m² | ASTM D256 | | |
| Thermal | Nominal Value | Unit | Test Method | | |

| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 70.0 | °C | ASTM D648 |
|--|---------------|---------|-------------|
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 1.0E+16 | ohms·cm | ASTM D257 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 115 to 120 | °C | |
| Drying Time | 6.0 to 8.0 | hr | |
| Processing (Melt) Temp | 230 to 255 | °C | |
| Mold Temperature | 60.0 to 100 | °C | |
| Injection Pressure | 70.0 to 100 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

