

CERTENE™ PE 30000

Polyethylene
Muehlstein

Message:

CERTENE™ PE 30000 is a Polyethylene material. It is available in North America.


General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (10% Igepal, F50)	< 1.00	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.8	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Flexural Modulus - 1% Secant	262	MPa	ASTM D790B
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	95.0	°C	ASTM D1525
Peak Melting Temperature	124	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT