

Sindustris PBT SV1081

Polybutylene Terephthalate

Sincerity Australia Pty Ltd.

Message:

Sindustris PBT SV1081 is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific for injection molding. Primary attribute of Sindustris PBT SV1081: High Viscosity.

Typical applications include:

- Film
- Hose/Tubing
- Optics/Lenses
- Sheet

General Information			
Features	General Purpose		
	High Viscosity		
Uses	Film		
	Optical Applications		
	Sheet		
	Tubing		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.2 to 2.1	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	53.9	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 150	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2260	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	83.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	57.0	°C	
1.8 MPa, Unannealed, 6.40 mm	154	°C	
Peak Melting Temperature	225	°C	ASTM D3418
RTI Elec	75.0	°C	UL 746

RTI Imp	75.0	°C	UL 746
RTI Str	75.0	°C	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	230 to 235	°C	
Middle Temperature	235 to 245	°C	
Front Temperature	235 to 245	°C	
Nozzle Temperature	240 to 250	°C	
Processing (Melt) Temp	240 to 250	°C	
Mold Temperature	40.0 to 80.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	225 to 245	°C	
Cylinder Zone 2 Temp.	230 to 250	°C	
Cylinder Zone 3 Temp.	240 to 260	°C	
Cylinder Zone 4 Temp.	240 to 260	°C	
Adapter Temperature	240 to 260	°C	
Melt Temperature	225	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.8 mm/min		
4.	2.8 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT