

Starflam M10009AP

Polypropylene Homopolymer
Eurostar Engineering Plastics

Message:

Starflam M10009AP is an Unfilled Flame Retardant high fluidity Polypropylene (Homo) Injection Molding Resin

General Information			
Features	Flame Retardant		
	High Flow		
	Homopolymer		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm³	ASTM D792
Melt Volume-Flow Rate (MVR) (230°C/5.0 kg)	20.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow (4.00 mm)	1.6	%	Internal Method
Water Absorption (23°C, 24 hr)	0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield	36.0	MPa	
Break	23.0	MPa	
Tensile Strain (Yield)	7.2	%	ISO 527-2/50
Flexural Modulus ¹	1900	MPa	ISO 178
Flexural Stress	51.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	4.0	kJ/m²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	44	kJ/m²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴			
0.45 MPa, Unannealed, 64.0 mm Span	103	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	57.0	°C	ISO 75-2/Af
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Tested by E2P)	V-2		UL 94
Glow Wire Flammability Index (1.60 mm)	850	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Rear Temperature	180 to 190	°C	

Middle Temperature	190 to 200	°C
Front Temperature	190 to 200	°C
Processing (Melt) Temp	190 to 200	°C
Mold Temperature	30.0 to 50.0	°C

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 80*10*4 |
| 3. | 80*10*4 |
| 4. | 80*10*4 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT