

HiFill® PBT GF30 BK

Polybutylene Terephthalate

Techmer Engineered Solutions

Message:

HiFill® PBT GF30 BK is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	134	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	193	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	215	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength ¹	20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information	Nominal Value		
TPCI #	9864111		
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Rear Temperature	232 to 274	°C	
Middle Temperature	232 to 274	°C	
Front Temperature	232 to 274	°C	

Processing (Melt) Temp	232 to 246	°C
Mold Temperature	65.6 to 82.2	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

NOTE

1.
- Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT