

Radilon® BGV/MIG 15/25 Natural 2.5

Polyamide 6

Radici Plastics

Message:

Radilon® BGV/MIG 15/25 Natural 2.5 is a Polyamide 6 (Nylon 6) material filled with 15% glass fiber and 25% mineral. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of Radilon® BGV/MIG 15/25 Natural 2.5 are:

Flame Rated

Heat Resistant

General Information				
Filler / Reinforcement		Glass Fiber,15% Filler by Weight Mineral,25% Filler by Weight		
Features		Good Heat Aging Resistance		
Appearance		Natural Color		
Resin ID (ISO 1043)		PA6-(GF15+M25)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.48	--	g/cm ³	ISO 1183
Water Absorption ¹ (Equilibrium, 23°C, 1.00 mm, 50% RH)	1.8 to 2.2	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9000	5200	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	115	75.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	5.0	%	ISO 527-2/1A/5
Flexural Modulus ²	8000	4800	MPa	ISO 178
Flexural Stress ³	180	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	45	70	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	210	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	--	°C	ISO 75-2/A
Melting Temperature ⁴	220	--	°C	ISO 3146
Flammability	Dry	Conditioned	Test Method	
Flame Rating	HB	--	UL 94	
NOTE				
1.	Saturation			

2.	2.0 mm/min
3.	2.0 mm/min
4.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

