

WPP PP PPC6TF1V-RXF

Polypropylene Copolymer

Washington Penn Plastic Co. Inc.

Message:

WPP PP PPC6TF1V-RXF is a polypropylene copolymer (PP Copoly) product, which contains 10% talc filler. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

Features include:

high liquidity

Copolymer

General Information			
Filler / Reinforcement	Talc filler, 10% filler by weight		
Features	Copolymer		
	High liquidity		
Uses	Application in Automobile Field		
Appearance	Available colors		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	31.0	MPa	ISO 527-2/50
Flexural Modulus ¹	1700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	63.0	°C	ISO 75-2/A
Additional Information			
Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

