

PrimoTek KM6100

Polybutylene Terephthalate

KMI Group Inc.

Message:

PrimoTek KM6100 is a Polybutylene Terephthalate (PBT) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30 to 1.32	g/cm ³	ASTM D792B
Melt Mass-Flow Rate (MFR) ¹	25 to 35	g/10 min	ASTM D1238
Color b	< 5.50		Internal Method
Color L	> 90.0		Internal Method
Intrinsic Viscosity	0.99 to 1.0	dl/g	Internal Method
Carboxyl End Groups	< 30.0	mol/t	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	50.0 to 60.0	MPa	ASTM D638
Tensile Elongation (Break)	> 200	%	ASTM D638
Flexural Strength	> 85.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ²	> 40	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	220 to 225	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (2.00 mm)	> 2.0	kV/mm	ASTM D149
NOTE			
1.	Procedure A		
2.	Notch A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT