

SHANGHAI SUSHENG 113C

Low Density Polyethylene
The Dow Chemical Company

Message:
DOW™ LDPE 113C is a Low Density Polyethylene Resin material. It is available in Latin America. Primary attribute of DOW™ LDPE 113C: Antiblock.
Typical application of DOW™ LDPE 113C: Food Contact Applications

General Information			
Additive	Antiblock		
Agency Ratings	FDA 21 CFR 177.1520(c) 2.1		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.923	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.8	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	0.10		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	
Tensile Strength			ASTM D882
MD : Yield,38 µm	12.0	MPa	
TD : Yield,38 µm	12.0	MPa	
MD : Break, 38 µm	21.0	MPa	
TD : Break, 38 µm	17.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 38 µm	300	%	
TD : Break, 38 µm	600	%	
Dart Drop Impact (38 µm)	100	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 38 µm	360	g	
TD : 38 µm	180	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 38.0 µm)	68		ASTM D2457
Haze (38.0 µm)	7.5	%	ASTM D1003
Injection	Nominal Value	Unit	
Processing (Melt) Temp	165	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

