

LNP™ LUBRICOMP™ LCL36 compound

Polyetheretherketone

SABIC Innovative Plastics Europe

Message:

LNP LUBRICOMP LCL36 is a compound based on Polyetheretherketone containing Carbon Fiber , PTFE. Added features of this material include Electrically Conductive, Internally Lubricated.

General Information			
UL YellowCard	E45329-101284426		
Filler / Reinforcement	Carbon Fiber		
Additive	PTFE Lubricant		
Features	Electrically Conductive		
	Lubricated		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13500	MPa	ISO 527-2/1
Tensile Stress (Break)	201	MPa	ISO 527-2/5
Tensile Strain (Break)	3.7	%	ISO 527-2/5
Flexural Modulus ¹	16300	MPa	ISO 178
Flexural Stress	267	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	9.0	kJ/m²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	35	kJ/m²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	> 300	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+3	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.700 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	349 to 360	°C	
Middle Temperature	366 to 377	°C	
Front Temperature	382 to 393	°C	

Processing (Melt) Temp	382 to 388	°C
Mold Temperature	138 to 166	°C
Back Pressure	0.344 to 0.689	MPa
Screw Speed	60 to 100	rpm

NOTE		
1.	2.0 mm/min	
2.	80*10*4	
3.	80*10*4	
4.	80*10*4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

