

Paryls® PPSU F1250

Polyphenylsulfone

Youju New Materials Co., Ltd.

Message:

PARYLS® PPSU F1250 pellets are supplied in cartons lining aluminum foil bag, which can be stored indefinitely, provided the packaging remains undamaged.

PARYLS® PPSU F1250 pellets absorb moisture very rapidly. Therefore, the pellets need to be dried at least 6h at 180 °C in a vacuum or dry air drier prior to processing.

General Information			
UL YellowCard	E472927-102108523		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (365°C/5.0 kg)	18 - 28	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4, ISO 2577
Transverse flow	1.0	%	ISO 294-4, ISO 2577
Flow	0.90	%	ISO 294-4, ISO 2577
Water Absorption (Equilibrium, 23°C, 50% RH)	0.35	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2270	MPa	ISO 527-2
Tensile Stress	70.0	MPa	ISO 527-2
Tensile Strain (Yield)	7.8	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	68	kJ/m ²	ISO 180/A

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	196	°C	ISO 75-2/A
Glass Transition Temperature ¹	220	°C	ISO 11357-2, DSC
CLTE - Flow (23°C)	5.5E-5	cm/cm/°C	ISO 11359-2

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ²	> 1.0E+15	ohms	IEC 60093
Volume Resistivity ³	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength ⁴	44	kV/mm	IEC 60243-1
Dielectric Constant			IEC 60250
100 Hz	3.80		IEC 60250

1 MHz	3.70		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	1.5E-3		IEC 60250
1 MHz	8.6E-3		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	180	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	350 - 390	°C	
Mold Temperature	140 - 180	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	180	°C	
Drying Time	6.0	hr	
Melt Temperature	350 - 390	°C	
Die Temperature	140 - 180	°C	
NOTE			
1.	10°C/min		
2.	100V		
3.	100V		
4.	K20/K20, (60*60*1 mm ³)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

