

SPESIN® KP212G30V0BLS

Polybutylene Terephthalate

Kolon Plastics, Inc.

Message:

SPESIN® KP212G30V0BLS is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E190675-100647280		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.70 to 1.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	132	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	8830	MPa	ASTM D790
Flexural Strength (23°C)	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	200	°C	
Peak Melting Temperature	224	°C	ASTM D3418
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	27	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150
Arc Resistance	110	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

