

Hanwha Total PP BJ700

Polypropylene Impact Copolymer
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

BJ700 is a high-flow block copolymer polypropylene resin for injection molding applications. This grade is designed to be processed in conventional injection molding equipment.

General Information			
UL YellowCard	E140331-222896		
Features	Block Copolymer		
	Rigidity, high		
	Impact resistance, high		
	High liquidity		
Uses	Home appliance components		
	Household goods		
	Car anti-collision bar		
	Car interior equipment		
	Car exterior decoration		
	Car dashboard		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	28.4	MPa	ASTM D638
Fracture	19.6	MPa	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Flexural Modulus	1320	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	39	J/m	ASTM D256
0°C	49	J/m	ASTM D256
23°C	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Optical	Nominal Value		Test Method
Gloss	60		ASTM D2457
Injection	Nominal Value	Unit	
Rear Temperature	170 - 200	°C	
Middle Temperature	180 - 220	°C	
Front Temperature	210 - 250	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Pressure	98.1 - 245	MPa	
Holding Pressure	78.5 - 226	MPa	
Injection instructions			

Cooling Time: 25 to 40 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

