Xuchuan A-7150/B-8260

Thermoplastic Polyurethane Elastomer (Polyester)

Xuchuan Chemical (Suzhou) Co., Ltd

Message:

Xuchuan A-7150/B-8260 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Applications of Xuchuan A-7150/B-8260 include consumer goods and marine applications. Primary characteristic: low temperature resistant.

General Information			
Features	High Elasticity Hydrolysis Resistant		
	Low Temperature Resistant		
Uses	Footwear		
U3C3	Marine Applications		
	Marine Applications		
Physical	Nominal Value	Unit	
Density	0.550 to 0.700	g/cm³	
Density			
A-7150 : 40°C	1.010 to 1.020	g/cm³	
B-8260 : 40°C	1.080 to 1.200	g/cm³	
Viscosity			
A-7150 : 40°C	1.00 to 1.40	Pa·s	
B-8260 : 40°C	0.700 to 1.10	Pa·s	
Ross Flex (-20°C) ¹	No Crack		
Cream Time	9.0 to 11.0	sec	
End of Rise Time	1.0 to 1.2	min	
Free Rise Foam Density	250 to 300	kg/m³	
Preheat Temperature			
Part A	50 to 60	°C	
Part B	50 to 60	°C	
Preheat Time			
Part A	6.0 to 8.0	hr	
Part B	8.0 to 12.0	hr	
Processing Temperature			
Part A	40 to 45	°C	
Part B	38 to 42	°C	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	55 to 65		
Elastomers	Nominal Value	Unit	
Tensile Strength (Break)	9.50 to 13.0	МРа	

Tensile Elongation (Break)	500 to 750	%	
Tear Strength	38.0 to 50.0	kN/m	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 100		
Part B	Mix Ratio by Weight: 94 to 95		
Demold Time	5.0 to 7.0	min	
Injection	Nominal Value	Unit	
Mold Temperature	45.0 to 55.0	°C	
NOTE			
1.	40000 cycles, Break length 4 mm		

40000 cycles, Break length 4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

