

Mar-Bal MB2000-5

Thermoplastic Polyester

Mar-Bal, Inc.

Message:

An excellent flame and track resistant material with excellent electrical and mechanical properties. Good dielectric strength and low shrink for close dimensional control.

General Information			
UL YellowCard	E80533-250706		
Filler / Reinforcement	Glass Fiber,5.0% Filler by Weight		
Features	Flame Retardant		
	Good Dimensional Stability		
	Good Electrical Properties		
	Low Shrinkage		
	Tracking Resistant		
UL File Number	E80533		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80 to 1.90	g/cm ³	ASTM D792
Bulk Factor	1.0		ASTM D1895
Molding Shrinkage - Flow	0.050 to 0.30	%	ASTM D955
Water Absorption (24 hr)	0.17	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	25 to 35		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	27.6 to 34.5	MPa	ASTM D638
Flexural Modulus	8960 to 11000	MPa	ASTM D790
Flexural Strength	55.2 to 75.8	MPa	ASTM D790
Compressive Modulus	359000 to 379000	MPa	ASTM D695
Compressive Strength	96.5 to 110	MPa	ASTM D695
Shear Strength	27.6 to 34.5	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80 to 130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	> 16	kV/mm	ASTM D149
Arc Resistance	> 240	sec	ASTM D495
Inclined-Plane Tracking	> 1000	min	ASTM D2303
Flammability	Nominal Value	Unit	Test Method

Flame Rating	V-0	UL 94
NOTE		

- Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

