

Wanthane® WHT-1570IC

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

TYPE: Polyester-based grade Extrusion and injection molding grade
FEATURES: Free of plasticizer, excellent abrasion and slip resistance, low temperature flexibility, good processability
Applications: Electronic Parts, rigid / flexible composite systems, tools, shoes, compounds, etc

General Information			
Features	Flexibility at low temperatures		
	Workability, good		
	Good wear resistance		
Uses	Electrical/Electronic Applications		
	Power/other tools		
	Composite		
	Footwear		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
DIN Abrasion	50.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	3.50	MPa	ASTM D412
300% strain	6.50	MPa	ASTM D412
Tensile Strength (Break)	30.0	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Tear Strength	75.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 24 hr	16	%	ASTM D395
70°C, 22 hr	48	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-40.0	°C	ASTM D3418
Vicat Softening Temperature	65.0	°C	ASTM D1525

Injection	Nominal Value	Unit
Drying Temperature	90 - 100	°C
Drying Time	2.0 - 3.0	hr
Suggested Max Moisture	0.030	%
Rear Temperature	180	°C
Middle Temperature	185	°C
Front Temperature	190	°C
Nozzle Temperature	195	°C
Mold Temperature	23	°C
Screw L/D Ratio	25.0:1.0 to 30.0:1.0	
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0	

Extrusion	Nominal Value	Unit
Drying Temperature	90 - 100	°C
Drying Time	2.0 - 3.0	hr
Suggested Max Moisture	0.030	%
Cylinder Zone 1 Temp.	175	°C
Cylinder Zone 2 Temp.	180	°C
Cylinder Zone 3 Temp.	185	°C
Cylinder Zone 4 Temp.	190	°C
Adapter Temperature	195	°C
Die Temperature	190	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT