

KIBISAN® PN-107 L125 FG

Styrene Acrylonitrile

CHI MEI CORPORATION

Message:

Food Contact SAN KIBISAN PN-107 L125 FG

Product Description: High clarity

General Information			
UL YellowCard	E56070-102699318		
Features	Definition, high		
	Compliance of Food Exposure		
RoHS Compliance	RoHS compliance		
Resin ID (ISO 1043)	>SAN		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.06	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	58.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.20 - 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield	65.0	MPa	ISO 527-2/50
Fracture	65.0	MPa	ISO 527-2/50
Tensile Strain (Break)	4.0	%	ISO 527-2/50
Flexural Modulus ¹	2600	MPa	ISO 178
Flexural Stress ²	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.0	kJ/m ²	ISO 179
Notched Izod Impact (23°C)	2.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			ISO 75-2/A
1.8 MPa, not annealed	88.0	°C	ISO 75-2/A
1.8 MPa, annealed	99.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	104	°C	ISO 306/A50
--	101	°C	ISO 306/B50
CLTE - Flow	3.6E-5 - 3.8E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

