

VALOX™ 7062HP resin

Polybutylene Terephthalate
SABIC Innovative Plastics Europe

Message:
ENDURAN 7062HP is a 38% mineral filled & FDA compliance injection moulding resin.

General Information			
Filler / Reinforcement	Mineral,38% Filler by Weight		
Agency Ratings	FDA Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.81	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (266°C/1.2 kg)	33	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)			ISO 1133
265°C/1.2 kg	21.0	cm ³ /10min	
265°C/2.16 kg	41.0	cm ³ /10min	
Molding Shrinkage - Flow (3.20 mm)	1.2 to 1.9	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.070	%	
Equilibrium, 23°C, 50% RH	0.070	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	140	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4130	MPa	ASTM D638
--	4200	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	53.0	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/5
Break ³	55.0	MPa	ASTM D638
Break	60.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	3.0	%	ASTM D638
Yield	3.0	%	ISO 527-2/5
Break ⁵	3.0	%	ASTM D638
Break	3.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	4480	MPa	ASTM D790
-- ⁷	3900	MPa	ISO 178

Flexural Stress			
--	100	MPa	ISO 178
Break, 50.0 mm Span ⁸	110	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	74.0	mg	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	2.0	kJ/m ²	
23°C	2.0	kJ/m ²	
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	33	kJ/m ²	
23°C	37	kJ/m ²	
Notched Izod Impact			
-30°C	26	J/m	ASTM D256
23°C	22	J/m	ASTM D256
-30°C ¹¹	3.0	kJ/m ²	ISO 180/1A
23°C ¹²	3.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	420	J/m	ASTM D4812
-30°C ¹³	30	kJ/m ²	ISO 180/1U
23°C ¹⁴	30	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	5.00	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	69.2	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁵	65.0	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	175	°C	ASTM D1525, ISO 306/B50, ISO 306/B120 ¹⁶
--	215	°C	ISO 306/A50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			
Flow : -40 to 40°C	9.0E-5	cm/cm/°C	ASTM E831
Flow : 23 to 80°C	9.0E-5	cm/cm/°C	ISO 11359-2
Flow : 23 to 150°C	1.1E-4	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	9.0E-5	cm/cm/°C	ASTM E831
Transverse : 23 to 80°C	9.0E-5	cm/cm/°C	ISO 11359-2
Transverse : 23 to 150°C	1.1E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.32	W/m/K	ISO 8302
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	2.0 to 4.0	hr	

Suggested Max Moisture	0.020	%
Hopper Temperature	40.0 to 60.0	°C
Rear Temperature	230 to 250	°C
Middle Temperature	240 to 260	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	245 to 270	°C
Processing (Melt) Temp	255 to 280	°C
Mold Temperature	60.0 to 100	°C

NOTE

1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4 sp=62mm
11.	80*10*4
12.	80*10*4
13.	80*10*4
14.	80*10*4
15.	120*10*4 mm
16.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT