

Starex SF-0505H

Methyl Methacrylate / ABS

SAMSUNG SDI CO., LTD.

Message:

Starex SF-0505H is a Methyl Methacrylate / ABS (MABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard		E115797-460972	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	17	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.30 to 0.60	%	ASTM D955, ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	113		ASTM D785, ISO 2039-2
Pencil Hardness ¹	F		JIS K5401
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	2400	MPa	ASTM D638
--	2400	MPa	ISO 527-2/50
Tensile Strength			
Yield ³	50.0	MPa	ASTM D638
Yield	56.0	MPa	ISO 527-2/50
Break ⁴	39.0	MPa	ASTM D638
Break	48.0	MPa	ISO 527-2/50
Tensile Elongation			
Break ⁵	11	%	ASTM D638
Break	5.6	%	ISO 527-2/50
Flexural Modulus			
-- ⁶	2300	MPa	ASTM D790
-- ⁷	2400	MPa	ISO 178
Flexural Strength			
-- ⁸	76.0	MPa	ASTM D790
-- ⁹	81.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁰ (23°C)	5.3	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	110	J/m	ASTM D256
23°C ¹¹	4.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			
0.45 MPa, Unannealed, 6.40 mm	92.0	°C	ASTM D648
0.45 MPa, Unannealed, 4.00 mm	84.0	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	84.0	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	73.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	94.0	°C	ISO 306/B50
--	96.0	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature			
--	85.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	190 to 200	°C	
Middle Temperature	210 to 220	°C	
Front Temperature	230 to 240	°C	
Nozzle Temperature	240	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	49.0 to 245	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	Condition: 500g		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	5.0 mm/min		
6.	2.8 mm/min		
7.	2.0 mm/min		
8.	2.8 mm/min		
9.	2.0 mm/min		
10.	Thickness: 4 mm		
11.	Thickness: 4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

