

Stanyl® 46HF4130

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® 46HF4130 is a Polyamide 46 (Nylon 46) material filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Important attributes of Stanyl® 46HF4130 are:

- Flame Rated
- Heat Stabilizer
- High Flow

General Information				
UL YellowCard		E43392-235028	E47960-240075	
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
		High Flow		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.3	--	%	
Flow	0.50	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.6	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	10000	6000	MPa	
120°C	5500	--	MPa	
160°C	5000	--	MPa	
180°C	4700	--	MPa	
200°C	4500	--	MPa	
Tensile Stress				ISO 527-2
Break	210	115	MPa	
Break, 120°C	125	--	MPa	
Break, 160°C	110	--	MPa	
Break, 180°C	95.0	--	MPa	
Break, 200°C	90.0	--	MPa	
Tensile Strain				ISO 527-2
Break	3.0	6.0	%	
Break, 120°C	5.5	--	%	
Break, 160°C	5.5	--	%	

Break, 180°C	5.5	--	%	
Break, 200°C	5.5	--	%	
Flexural Modulus	9000	5500	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	12	12	kJ/m ²	
23°C	13	17	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	60	kJ/m ²	
23°C	60	90	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	290	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.5E-5	--	cm/cm/°C	
Transverse	6.0E-5	--	cm/cm/°C	
Thermal Index - 5000 hrs	177	--	°C	IEC 60216
Flammability	Dry	Conditioned		Test Method
Flammability Classification				IEC 60695-11-10, -20
0.750 mm	HB	--		
1.50 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 310		°C	
Middle Temperature	300 to 315		°C	
Front Temperature	300 to 315		°C	
Nozzle Temperature	300 to 310		°C	
Processing (Melt) Temp	310 to 320		°C	
Mold Temperature	60.0 to 120		°C	
Injection Rate	Moderate-Fast			
Back Pressure	1.00		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

