

Nipol® AR 71

Rubber

Zeon Corporation

Message:

Acrylic rubber, a specialty rubber that uses alkyl acrylate as a primary component, affords outstanding resistance to heat, oil (lubricants) and weather. It withstands use over long periods of time at high temperatures of 150 to 175°C, providing outstanding heat resistance at a level just below fluoro-contained rubber and silicone rubber. Therefore, it is used in a wide range of applications, such as hoses, tubes, seals, and gaskets for automobiles and general industrial machinery. A new grade featuring improved heat resistance has been recently developed and is expected to support even more extensive applications in the future.

Characteristics & Applications

Fast curing type suitable for molded products like seals and gaskets.

General Information			
Features	Fast Cure		
	Good Weather Resistance		
	High Heat Resistance		
	Oil Resistant		
Uses	Gaskets		
	Seals		
Physical	Nominal Value	Unit	
Specific Gravity	1.11	g/cm ³	
Mooney Viscosity	50	MU	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-15.0	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

