

Durethan® B 30 S F30 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, non-reinforced, injection molding, flame retardant

General Information			
UL YellowCard	E245249-100654671		
Additive	Flame retardancy		
Features	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA FR (17)		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.35	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	1.1	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.40	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	1.1	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.40	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3600	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	70.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	3.7	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	9.0	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	3200	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% strain, 23°C	100	MPa	ISO 178/A
23°C ⁶	110	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.5	%	ISO 178/A
ISO Shortname	PA 6, GFHR, 14-040		ISO 1874
Admissible Residence Time at Tmax	> 10.0	min	
Residual Moisture Content	0.030 - 0.12	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	130	kJ/m ²	ISO 179/1eU

23°C	150	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	100	kJ/m ²	ISO 180/1U
23°C	120	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	70.0	°C	ISO 75-2/A
Melting Temperature ⁸	222	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-0		UL 94
0.750 mm	V-0		UL 94
1.50 mm	V-0		UL 94
2.00 mm	5VA		UL 94
3.00 mm	5VA		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.800 mm	960	°C	IEC 60695-2-12
1.50 mm	960	°C	IEC 60695-2-12
3.00 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	825	°C	IEC 60695-2-13
1.50 mm	825	°C	IEC 60695-2-13
3.00 mm	800	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0	°C	
Drying Time - Dry Air Dryer	2.0 - 6.0	hr	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

