

Drystar™ 0325

Copolyester
Eastman Chemical Company

Message:

Eastman is pleased to announce the launch of DRYSTAR* copolyesters. This new product-line is designed to meet the needs of converters seeking value-added solutions to their drying requirements of copolyesters. Eastman’s copolyesters are highly valued for their excellent balance of properties such as superior aesthetics, impact strength, and chemical resistance. These properties can be optimally realized when the resins are properly dehydrated in accordance to recommended drying conditions and equipment.

Recognizing this value, Eastman conceived Drystar™ copolyesters to allow converters with limited access to desiccant dryers to achieve these optimizations. In addition, some converters with desiccant dryers may still find Drystar™ copolyesters value-adding to attain production flexibility and cost saving by removing the drying process prior to injection molding, profile extruding, or extrusion blow molding copolyesters. The initial launch comprises of the commercialization of four grades of Drystar™ copolyesters and Eastman has on-going program to extend this strategic product-line in the future.

*DRYSTAR is only available in the Asia Pacific Region.

General Information			
Features	Good Chemical Resistance		
	Good Impact Resistance		
	Pleasing Surface Appearance		
Forms	Pellets		
Processing Method	Extrusion Blow Molding		
	Injection Molding		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	2030	MPa	ASTM D638
23°C	2000	MPa	ISO 527-2
Tensile Strength			
Yield, 23°C	50.0	MPa	ASTM D638
Yield, 23°C	48.0	MPa	ISO 527-2
Break, 23°C	30.0	MPa	ASTM D638
Break, 23°C	29.0	MPa	ISO 527-2
Tensile Elongation			
Yield, 23°C	4.4	%	ASTM D638
Yield, 23°C	4.0	%	ISO 527-2
Break, 23°C	180	%	ASTM D638

Break, 23°C	200	%	ISO 527-2
Flexural Modulus			
23°C	2060	MPa	ASTM D790
23°C	2100	MPa	ISO 178
Flexural Strength			
23°C	68.0	MPa	ASTM D790
23°C	67.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
-40°C	40	J/m	ASTM D256
23°C	110	J/m	ASTM D256
-40°C	4.4	kJ/m ²	ISO 180
23°C	9.4	kJ/m ²	ISO 180
Unnotched Izod Impact			
-40°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	70.0	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	62.0	°C	ASTM D648, ISO 75-2/A
Optical	Nominal Value	Unit	Test Method
Transmittance (Total)	90.0	%	ASTM D1003
Haze	0.20	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	71.0	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	16.0 to 38.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT