

Lupolen 4021 K RM Black

Medium Density Polyethylene

LyondellBasell Industries

Message:

Lupolen 4021 K RM Black is the black compound version of the new generation hexene linear medium-density polyethylene LP 4021 K RM for rotational molding. Typical customer applications include large tanks including underground and infrastructure applications. The product exhibits outstanding ESCR combined with high impact at low temperatures and improved UV resistance. Lupolen 4021 K RM Black is a fully UV-stabilized and pelletized polymer. Tests have shown that this material is resisting against the harmful effect of biodiesel fuel.**
It is not intended for use in medical and pharmaceutical applications.
** Resistance is based on our latest patented technology

General Information			
Additive	UV stabilizer		
Features	Low warpage		
	High ESCR (Stress Cracking Resistance)		
	Workability, good		
	Low temperature impact resistance		
Uses	Industrial application		
	Industrial water tank		
	Fuel Tank		
Appearance	Black		
Forms	Particle		
Processing Method	rotomolding		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.940	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance	> 1000	hr	ASTM D1693B
FNCT ² (50°C)	2.1	day	ISO 16770
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	750	MPa	ISO 527-2
Tensile Stress (Yield)	19.0	MPa	ISO 527-2
Tensile Strain (Yield)	9.0	%	ISO 527-2
Films	Nominal Value	Unit	Test Method
Tensile Elongation (Break)	> 450	%	ISO 527-3
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength			ISO 8256/1A
-30°C	120	kJ/m ²	ISO 8256/1A
23°C	265	kJ/m ²	ISO 8256/1A
Thermal	Nominal Value	Unit	Test Method

Vicat Softening Temperature	114	°C	ISO 306/A50
Extrusion	Nominal Value	Unit	
Melt Temperature	180 - 210	°C	
Extrusion instructions			
Processing: Recommended range for PIAT (Peak Internal Air Temperature) is 180 - 210 °C. PIAT should not exceed 225 °C.			
NOTE			

- | | |
|----|---|
| 1. | Density value is given of the base polymer. Final density of the black product is higher due to pigmentation. |
| 2. | 6.0 MPa, 2% Arkopal N100 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

