

TEKAMID™ TB120LW

Polyamide 6

Mando Advanced Materials Co., Ltd.

Message:

TB120LW is a unreinforced polyamide 6.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.4	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.6	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	73.5	MPa	ASTM D638
Tensile Elongation ² (Break)	80	%	ASTM D638
Flexural Modulus ³	2430	MPa	ASTM D790
Flexural Strength ⁴	98.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	44	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	175	°C	ASTM D648
1.8 MPa, not annealed	70.0	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	4.0 - 5.0	hr	
Rear Temperature	225 - 245	°C	
Middle Temperature	230 - 260	°C	
Front Temperature	240 - 270	°C	
Nozzle Temperature	240 - 270	°C	
Processing (Melt) Temp	240 - 270	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection instructions			
Injection Speed: 20 to 50%Injection Pressure - 1st: 30 to 60%Injection Pressure - 2nd: 30 to 60%Injection Pressure - Back Pressure: 0 to 20%			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

