

Witcom PC/ABS AS-S-LM

Polycarbonate + ABS

Witcom Engineering Plastics B.V.

Message:

Meets ATEX-regulations

General Information			
Additive	Antistatic property		
Features	Laser marking		
	Antistatic property		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage - Flow (3.00 mm)	0.50 - 0.90	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	< 48.0	MPa	ISO 527-2
Tensile Strain (Break)	> 100	%	ISO 527-2
Flexural Modulus	1000	MPa	ISO 178
Flexural Stress	43.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	60	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	95.0	°C	ISO 75-2/A
RTI Imp (3.00 mm)	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8 - 1.0E+9	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (3.20 mm)	HB		IEC 60695-11-10, -20
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	250 - 280	°C	
Mold Temperature	50.0 - 80.0	°C	
Injection Rate	Moderate		
Back Pressure	0.00 - 1.00	MPa	
Injection instructions			

Screw speed: 0.1 - 0.2 m/sInjection pressure: Keep to a minimumHold pressure: Keep to a minimum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

