

RIALENE® P 100 SGF30 ST F V-0 natural

Polypropylene

RIA-Polymers GmbH

Message:

RIALENE P 100 SGF30 ST F V-0 natural is a semi-crystalline thermoplastic construction material based on polypropylene (PP), reinforced with 30 % special glass fiber (SGF) which is optimized linked to the polymer matrix.

RIALENE P 100 SGF30 ST F V-0 natural will be processed by injection molding and has halogen- and heavy metal-free fire protection equipment.

RIALENE P 100 SGF30 ST F V-0 natural is characterized by the following properties:

UL 94 V-0 listed at 1.5 mm

Conform to GWIT 800 °C at 1.5 mm

excellent rigidity and strength with good elongation behavior

excellent thermo-mechanical properties

halogen- and heavy metal-free flame retardants (conform to WEEE and RoHS)

very low smoke density

no corrosion during processing

General Information			
UL YellowCard	E257171-101026977		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Flame retardancy		
Features	Semicrystallization		
	Rigidity, high		
	High strength		
	Halogen-free		
	Flame retardancy		
Agency Ratings	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PP SGF30		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	4.30	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	0.30 - 0.50	%	ISO 294-4
Flow direction	0.20 - 0.30	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8750	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield	95.0	MPa	ISO 527-2/5
Fracture	94.0	MPa	ISO 527-2/5
Tensile Strain			ISO 527-2/5

Yield	3.6	%	ISO 527-2/5
Fracture	3.9	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	11	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	48	kJ/m ²	ISO 179/1eU
23°C	49	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	160	°C	ISO 75-2/B
1.8 MPa, not annealed	151	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+17	ohms · cm	IEC 60093
Dielectric Strength	41	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-2		UL 94
1.50 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Glow Wire Flammability Index (1.50 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.50 mm)	800	°C	IEC 60695-2-13
Additional Information			
Mechanical values determined after storage > 16 h at standard conditioning atmosphere (23 °C / 50 % rel. h.)			
Injection	Nominal Value	Unit	
Drying Temperature	95.0	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.030	%	
Hopper Temperature	50.0 - 70.0	°C	
Rear Temperature	220 - 230	°C	
Middle Temperature	220 - 240	°C	
Front Temperature	220 - 250	°C	
Nozzle Temperature	220 - 250	°C	
Processing (Melt) Temp	220 - 250	°C	
Mold Temperature	40.0 - 60.0	°C	
Injection Rate	Slow-Moderate		
Back Pressure	0.500 - 5.00	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

