

Hytrel® 4556

THERMOPLASTIC POLYESTER ELASTOMER

DuPont Performance Polymers

Message:

45 Shore D High Performance Polyester Elastomer

General Information			
UL YellowCard	E41938-234582		
Additive	UV Stabilizer		
Uses	Film		
	Profiles		
	Sheet		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Casting		
	Coating		
	Extrusion		
	Film Extrusion		
	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (TPE) (ISO 11403-1)		
	Tensile Modulus vs. Temperature, Dynamic (ISO 11403-1)		
Part Marking Code (ISO 11469)	>TPC-ET<		
Resin ID (ISO 1043)	TPC-ET		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/2.16 kg)	8.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/2.16 kg)	7.50	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	1.1	%	
Water Absorption			

24 hr	0.60	%	ASTM D570
23°C, 24 hr, 2.00 mm	0.60	%	ISO 62
Equilibrium, 23°C, 2.00 mm, 50% RH	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	45		
Shore D, 15 sec	42		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	85.0	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	34.0	MPa	
10% Strain	5.70	MPa	
50% Strain	9.80	MPa	
100% Strain	11.0	MPa	
300% Strain	17.0	MPa	
Tensile Strain (Break)	> 300	%	ISO 527-2
Nominal Tensile Strain at Break	740	%	ISO 527-2
Flexural Modulus	87.0	MPa	ISO 178
Abrasion Resistance	130	mm ³	ISO 4649
Effective Thermal Diffusivity	0.0544	cSt	
Elastomers	Nominal Value	Unit	Test Method
Tear Strength			ISO 34-1
Across Flow	120	kN/m	
Flow	120	kN/m	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	No Break		
-30°C	No Break		
23°C	No Break		
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-40°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	50.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	35.0	°C	ISO 75-2/A
Brittleness Temperature	-100	°C	ISO 974
Glass Transition Temperature ¹	-45.0	°C	ISO 11357-2
Vicat Softening Temperature			

--	155	°C	ISO 306/A50
--	60.0	°C	ISO 306/B50
Melting Temperature ²	193	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.7E-4	cm/cm/°C	
Flow : -40 to 23°C	2.2E-4	cm/cm/°C	
Transverse	1.9E-4	cm/cm/°C	
Transverse : -40 to 23°C	2.1E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.0E+14	ohms	IEC 60093
Volume Resistivity	8.0E+12	ohms·cm	IEC 60093
Electric Strength	19	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.80		
1 MHz	4.50		
Dissipation Factor			IEC 60250
100 Hz	9.5E-3		
1 MHz	0.030		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	HB		
3.00 mm	HB		
Oxygen Index	20	%	ISO 4589-2
NOTE			
1.	10°C/min		
2.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT