

Kingfa PA66-RG201

Polyamide 66

Kingfa

Message:

Kingfa PA66-RG201 is a polyamide 66 (nylon 66) material, which contains a 20% glass fiber reinforced material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main features of Kingfa PA66-RG201 are:

flame retardant/rated flame

Flame Retardant

high strength

Heat resistance

The typical application areas of Kingfa PA66-RG201 are: electrical/electronic applications

General Information			
UL YellowCard	E171666-101047311	E171666-101205190	
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	No frost		
	High strength		
	Good electrical performance		
	Heat resistance, high		
	Flame retardancy		
Uses	Connector		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 23°C	0.50	%	ASTM D955
Transverse flow: 23°C	1.1	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.60	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	135	MPa	ASTM D638
Tensile Elongation ² (Break)	2.2	%	ASTM D638
Flexural Modulus ³	6800	MPa	ASTM D790
Flexural Strength ⁴	185	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, unannealed, 6.40mm	255	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	246	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 110	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	255 - 275	°C	
Middle Temperature	260 - 290	°C	
Front Temperature	270 - 300	°C	
Processing (Melt) Temp	275 - 300	°C	
Mold Temperature	50.0 - 70.0	°C	
Injection Rate	Moderate-Fast		
Injection instructions			
Processing Temperature Limit: 310°C			
NOTE			
1.	10 mm/min		
2.	10 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT