

Lucky Enpla LPC1001F 9306

Polycarbonate
Lucky Enpla Co LTD

Message:

Lucky Enpla LPC1001F 9306 is a polycarbonate (PC) product. It is available in North America, Europe or Asia Pacific. The main characteristics are: flame retardant/rated flame.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60 - 0.65	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	53.0	MPa	ASTM D638
Flexural Modulus ²	2280	MPa	ASTM D790
Flexural Strength ³	82.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	590	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	122	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	3.0 - 5.0	hr	
Rear Temperature	270 - 290	°C	
Middle Temperature	280 - 300	°C	
Front Temperature	285 - 305	°C	
Nozzle Temperature	295 - 315	°C	
Mold Temperature	50.0 - 80.0	°C	
Back Pressure	0.490 - 2.94	MPa	
Screw Speed	30 - 50	rpm	
Injection instructions			
Resin Temperature: 280-300°CInjection Pressure (1st Pressure): 700-1200 kg/cm²Injection Pressure (2nd Pressure): 500-900 kg/cm²			
NOTE			
1.	50 mm/min		
2.	10 mm/min		
3.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

