

POCAN® T 7331 000000

Polybutylene Terephthalate + PET

LANXESS GmbH

Message:

PBT+PET, 30 % glass fibers, injection molding, improved surface finish, increased temperature peak load

General Information			
UL YellowCard	E245249-474062		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Surface Finish		
	Medium Heat Resistance		
Processing Method	Injection Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
	1.55		
Density (23°C)	1.55	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 270°C, 2.00 mm ¹	0.90	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	%	
Flow : 270°C, 2.00 mm ³	0.30	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Water Absorption			ISO 62
	0.30		
Saturation, 23°C	0.30	%	

0.10

Equilibrium, 23°C, 50% RH	0.10	%	
Viscosity Number (Reduced Viscosity)	91.0	ml/g	ISO 1628
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	200	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	9980	MPa	ASTM D638
23°C	10400	MPa	ISO 527-2/1
Tensile Strength			
Break, 23°C	123	MPa	ASTM D638
Break, 23°C	145	MPa	ISO 527-2/5
Tensile Elongation			
Break, 23°C	2.5	%	ASTM D638
Break, 23°C	2.8	%	ISO 527-2/5
Tensile Creep Modulus			
			ISO 899-1
1 hr	10000	MPa	
1000 hr	8500	MPa	
Flexural Modulus			
23°C	8550	MPa	ASTM D790
23°C ⁵	10300	MPa	ISO 178/A
Flexural Strength			
23°C	207	MPa	ASTM D790
23°C ⁶	230	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	3.0	%	ISO 178/A
Halving Interval			
			IEC 60216
Electric Strength	10.2	°C	
Tensile Impact Strength	13.5	°C	
Tensile Strength	10.2	°C	
Temperature Index			
			IEC 60216
Electric Strength, 20000 hr	155	°C	
Tensile Impact Strength, 20000 hr	140	°C	
Tensile Strength, 20000 hr	155	°C	
Burning Behavior ⁸	passed		ISO 3795
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT+PET, GHMR, 09-100, GF30		ISO 7792

0.0 to 0.020

Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m ²	
23°C	65	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	55	kJ/m ²	
23°C	55	kJ/m ²	
Multi-Axial Instrumented Impact Energy (23°C)	2.10	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force (23°C)	650	N	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B120
Ball Pressure Test (220°C)	Pass		IEC 60695-10-2
Melting Temperature ⁹	225 to 250	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	3.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	9.0E-5	cm/cm/°C	
Thermal Conductivity (23°C)	0.27	W/m/K	ISO 8302
RTI Elec	140	°C	UL 746
RTI Imp	125	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Electric Strength (23°C, 1.00 mm)	27	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	4.00		
23°C, 1 MHz	3.80		
Comparative Tracking Index (Solution A)	250	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ¹⁰	21	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
	4.0 to 8.0		
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 90°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 90°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	US-FMVSS302		
9.	10°C/min		
10.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

