

KOPLA PA6 KRE1010

Polyamide 6 + ABS

KOPLA Co., Ltd.

Message:

KOPLA PA6 KRE1010 is a Polyamide 6 + ABS (Nylon 6+ABS) material. It is available in Asia Pacific.

Important attributes of KOPLA PA6 KRE1010 are:

Flame Rated

Good Toughness

Typical application of KOPLA PA6 KRE1010: Electrical/Electronic Applications

General Information			
Features	Good Toughness		
	High Elasticity		
Uses	Connectors		
	Electrical Parts		
	Wheels		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8 to 2.4	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.3	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	52.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 100	%	ASTM D638
Flexural Modulus (23°C)	1670	MPa	ASTM D790
Flexural Strength (23°C)	74.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	460	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	170	°C	
1.8 MPa, Unannealed	50.0	°C	
Melting Temperature	220	°C	
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+14	ohms · cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.00		ASTM D150

Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

