

Rotec® ABS 3001 TR-AC

Acrylonitrile Butadiene Styrene

ROMIRA GmbH

Message:

Rotec® ABS 3001 TR-AC is an acrylonitrile butadiene styrene (ABS) material. This product is available in Europe.

Rotec® The main features of ABS 3001 TR-AC are:

flame retardant/rated flame

Transparency

General Information			
Features	Good liquidity		
	Definition, high		
Appearance	Clear/transparent		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.09	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	24	g/10 min	ISO 1133
Molding Shrinkage (23°C)	0.30 - 0.60	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2100	MPa	ISO 527-2/1
Tensile Stress (23°C)	43.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	30	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2050	MPa	ISO 178
Flexural Stress ² (23°C)	66.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.7	kJ/m²	ISO 179/1eA
23°C	15	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	82.0	°C	ISO 75-2/A
Vicat Softening Temperature	94.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

