

RTP 300 TC-C-20

Polycarbonate
RTP Company

Message:
Thermally Conductive - Electrically Conductive

General Information			
Features	Conductivity		
	Heat conduction		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Moisture Content	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6890	MPa	ASTM D638
Tensile Strength	41.4	MPa	ASTM D638
Tensile Elongation (Yield)	< 1.0	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	66.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	27	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	96	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	129	°C	ASTM D648
Thermal Conductivity			
-- ¹	1.3	W/m/K	ASTM E1530
-- ²	5.0	W/m/K	ASTM E1461
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+4	ohms	ASTM D257
Volume Resistivity	< 1.0E+2	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Dew Point	< -34.4	°C	
Processing (Melt) Temp	288 - 321	°C	
Mold Temperature	65.6 - 107	°C	
Injection Pressure	68.9 - 124	MPa	

Injection instructions

Desiccant Type Dryer Required.

NOTE

- | | |
|----|---------------|
| 1. | Through-plane |
| 2. | In-plane |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

