

Starex SV-0165 U

Acrylonitrile Butadiene Styrene

SAMSUNG SDI CO., LTD.

Message:

Starex SV-0165 U is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
220°C/10.0 kg	8.2	g/10 min	ASTM D1238
220°C/10.0 kg	8.8	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	109		ASTM D785
R-Scale	112		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/50
Tensile Strength			
Yield ¹	39.0	MPa	ASTM D638
Yield	51.0	MPa	ISO 527-2/50
Break	38.0	MPa	ISO 527-2/50
Tensile Strain (Break)	12	%	ISO 527-2/50
Flexural Modulus ²	2800	MPa	ISO 178
Flexural Stress ³	81.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁴ (23°C)	17	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 6.35 mm	220	J/m	ASTM D256
23°C ⁵	21	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 4.00 mm	94.0	°C	ISO 75-2/B
0.45 MPa, Annealed	103	°C	ISO 75-2/B
1.8 MPa, Unannealed, 4.00 mm	81.0	°C	ISO 75-2/A
1.8 MPa, Annealed, 4.00 mm	99.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	100	°C	ISO 306/B50
--	103	°C	ISO 306/B120

Injection	Nominal Value	Unit
Drying Temperature		
--	80.0	°C
Desiccant Dryer	80.0	°C
Drying Time		
--	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	160 to 180	°C
Middle Temperature	190 to 200	°C
Front Temperature	210 to 220	°C
Nozzle Temperature	230	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	49.0 to 147	MPa
Back Pressure	0.490 to 1.96	MPa
Screw Speed	50 to 150	rpm

NOTE

1. 5.0 mm/min
2. 2.0 mm/min
3. 2.0 mm/min
4. Thickness: 4 mm
5. Thickness: 4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

