

Multilon® TN-3411V

Polycarbonate + ABS

TEIJIN LIMITED

Message:

PC/ABS polymer alloy

General Information			
UL YellowCard	E98529-253618	E244324-101599310	
Features	Flame Retardant		
Uses	Electrical Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2650	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	65.0	MPa	
Break	50.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	3.0	%	
Break	110	%	
Flexural Modulus ¹	2800	MPa	ISO 178
Flexural Stress ²	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	40	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	107	°C	ISO 75-2/B
1.8 MPa, Unannealed	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	109	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	8.0E-5	cm/cm/°C	
Transverse	8.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
2.50 mm	5VB		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

