

# Durez® 31906 (Compression)

Phenolic

Sumitomo Bakelite North America, Inc.

## Message:

Durez 31906 Black Phenolic is a medium impact, molding compound. It is designed for applications where additional mechanical strength is required.

General Information			
Features	Good strength		
	Medium impact resistance		
Appearance	Black		
Forms	Particles		
Processing Method	Resin transfer molding		
	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.55	g/cm <sup>3</sup>	ASTM D1895
Molding Shrinkage - Flow	0.60	%	ASTM D6289
Water Absorption	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8300	MPa	ASTM D638
Tensile Strength	55.0	MPa	ASTM D638
Flexural Strength	90.0	MPa	ASTM D790
Compressive Strength	214	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	204	°C	ASTM D648
RTI Elec (3.00 mm)	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+12	ohms · cm	ASTM D257
Dielectric Strength			ASTM D149
-- 1	13	kV/mm	ASTM D149
-- 2	11	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	6.00		ASTM D2520
Dissipation Factor (1 MHz)	0.060		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

1.50 mm	HB	UL 94
3.00 mm	HB	UL 94
6.00 mm	V-0	UL 94
Thermoset	Nominal Value	Unit
Shelf Life	52	wk
Additional Information		
Test Specimens Molded at 340-350°F Typical transfer-molded shrinkage is 0.007 in/in		
NOTE		
1.	Method A (short time)	
2.	Method B (step by step)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT