

XANTAR® MX 1001

Polycarbonate
Mitsubishi Engineering-Plastics Corp

Message:
Impact Modified, Flame Retardant, Good Flow

General Information			
UL YellowCard	E340159-100746656		
Additive	Flame Retardant		
	Impact Modifier		
Features	Flame Retardant		
	Good Flow		
	Impact Modified		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.60	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.35	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2
Tensile Stress (Yield)	55.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	40	kJ/m ²	ISO 180/4A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	135	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow	6.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	29	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	2.90		
1 MHz	2.80		
Dissipation Factor			IEC 60250
100 Hz	6.6E-4		
1 MHz	9.2E-3		
Comparative Tracking Index (CTI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.750 mm	V-0		
1.50 mm	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	960	°C	
3.00 mm	960	°C	
Oxygen Index	35	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

