

HONES® PA66 GF30

Polyamide 66

Guangdong Shunde Hones Polymer Material Co., Ltd.

Message:

Technology characteristics: 30% Glass fiber reinforced, flame retardant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	120	MPa	ASTM D638
Flexural Strength	210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	85	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	250	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (2.00 mm)	30	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.20		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	130	°C	
Drying Time	4.0	hr	
Rear Temperature	220 to 265	°C	
Middle Temperature	260 to 270	°C	
Front Temperature	260 to 270	°C	
Nozzle Temperature	260 to 270	°C	
Mold Temperature	60.0 to 90.0	°C	
Injection Pressure	60.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

