Pier One PC/ABS C1200 BK

Polycarbonate + ABS

Pier One Polymers, Inc.

Message:

Pier One PC/ABS C1200 BK is a Polycarbonate + ABS (PC+ABS) material. It is available in North America for injection molding.

General Information			
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12 to 1.20	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/3.8 kg)	5.0 to 10	g/10 min	ASTM D1238
Ash Content	0.0	%	ASTM D4218
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (23°C)	48.3 to 68.9	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 30	%	ASTM D638
Flexural Modulus ² (23°C)	1860 to 2550	MPa	ASTM D790
Flexural Strength ³ (23°C)	62.1 to 96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	430 to 640	J/m	ASTM D256
NOTE			
1.	Goal 8500 psi		
2.	Goal 325000 psi		
3.	Goal 12000 psi		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

