

LEXAN™ HP2 resin

Polycarbonate

SABIC Innovative Plastics

Message:

Med/high flow polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO and steam sterilizable. Contains mold release.

General Information			
UL YellowCard	E207780-100478265		
Additive	demoulding		
Features	Ethylene oxide disinfection		
	High liquidity		
	Biocompatibility		
	Disinfect with steam		
Uses	Drug		
	Medical/nursing supplies		
Agency Ratings	ISO 10993		
	USP Class VI		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.20	g/cm ³	ASTM D792
--	1.19	g/cm ³	ASTM D792
Specific Volume	0.830	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ASTM D570
24 hr	0.15	%	ASTM D570
Equilibrium, 23°C	0.35	%	ASTM D570
Equilibrium, 100°C	0.58	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	70		ASTM D785
Class r	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			

-- ¹	2370	MPa	ASTM D638
--	2350	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	62.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Fracture ³	68.0	MPa	ASTM D638
Fracture	65.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Fracture ⁵	130	%	ASTM D638
Fracture	100	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2340	MPa	ASTM D790
-- ⁷	2300	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0mm span ⁸	96.0	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	35	kJ/m ²	ISO 179/2C
Notched Izod Impact			
23°C	690	J/m	ASTM D256
-30°C ⁹	10	kJ/m ²	ISO 180/1A
23°C ¹⁰	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Energy at Peak Load)	62.0	J	ASTM D3763
Dart Drop Impact (23°C)	169	J	ASTM D3029
Tensile Impact Strength ¹¹	546	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	137	°C	ASTM D648
0.45 MPa, unannealed, 100 mm span ¹²	133	°C	ISO 75-2/Be
1.8 MPa, unannealed, 6.40mm	129	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹³	122	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	154	°C	ASTM D1525 ¹⁴
--	140	°C	ISO 306/B50
--	141	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow			

-40 to 95°C	6.8E-5	cm/cm/°C	ASTM E831
23 to 80°C	7.0E-5	cm/cm/°C	ISO 11359-2
Specific Heat	1250	J/kg/°C	ASTM C351
Thermal Conductivity			
--	0.19	W/m/K	ASTM C177
--	0.20	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	> 1.0E+17	ohms · cm	ASTM D257
--	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength			
3.20 mm, in Air	15	kV/mm	ASTM D149
3.20mm, in oil	17	kV/mm	IEC 60243-1
Dielectric Constant			
50 Hz	3.17		ASTM D150
60 Hz	3.17		ASTM D150
1 MHz	2.96		ASTM D150
50 Hz	2.70		IEC 60250
60 Hz	2.70		IEC 60250
1 MHz	2.70		IEC 60250
Dissipation Factor			
50 Hz	9.0E-4		ASTM D150
60 Hz	9.0E-4		ASTM D150
1 MHz	0.010		ASTM D150, IEC 60250
50 Hz	1.0E-3		IEC 60250
60 Hz	1.0E-3		IEC 60250
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 1		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.47 mm)	HB		UL 94
Oxygen Index	25	%	ISO 4589-2
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance (2540 µm)	88.0	%	ASTM D1003
Haze (2540 µm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	

Drying Temperature	121	°C
Drying Time	3.0 - 4.0	hr
Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 - 60	%
Rear Temperature	260 - 282	°C
Middle Temperature	271 - 293	°C
Front Temperature	282 - 304	°C
Nozzle Temperature	277 - 299	°C
Processing (Melt) Temp	282 - 304	°C
Mold Temperature	71.1 - 93.3	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

1. 50 mm/min
2. Type 1, 50mm/min
3. Type 1, 50mm/min
4. Type 1, 50mm/min
5. Type 1, 50mm/min
6. 1.3 mm/min
7. 2.0 mm/min
8. 1.3 mm/min
9. 80*10*4
10. 80*10*4
11. Type S
12. 120*10*4 mm
13. 120*10*4 mm
14. 标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT