

YUNGSOX® PP 5060T

Polypropylene Random Copolymer

Formosa Polypropylene

Message:

YUNGSOX® PP 5060T is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific.

Important attributes of YUNGSOX® PP 5060T are:

Flame Rated

Clarity

Copolymer

Good Aesthetics

Typical applications include:

Containers

Engineering/Industrial Parts

Film

Food Contact Applications

General Information			
UL YellowCard	E216959-100060468		
Features	Good Surface Finish		
	High Clarity		
	Random Copolymer		
Uses	Containers		
	Film		
	Profiles		
	Transparent or Translucent Parts		
Agency Ratings	FDA 21 CFR 177.1520		
UL File Number	E216959		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ISO 1133
Molding Shrinkage	1.3 to 1.7	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	27.5	MPa	ISO 527-2
Tensile Strain (Break)	300	%	ISO 527-2
Flexural Modulus	932	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	88	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	125	°C	ISO 306
Melting Temperature	146	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

