

Plexiglas® Diffuse V045-68193

Polymethyl Methacrylate Acrylic

Altuglas International of Arkema Inc.

Message:

Plexiglas® Diffuse V045-68193 is a Polymethyl Methacrylate Acrylic product. It is available in North America. Primary characteristic: flame rated.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	1.8	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	83		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2930	MPa	ASTM D638
Tensile Strength (Yield)	60.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength (Yield)	91.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ¹			ASTM D648
0.45 MPa, Annealed	93.3	°C	
1.8 MPa, Annealed	90.6	°C	
Vicat Softening Temperature			
--	104	°C	ASTM D1525 ²
--	98.9	°C	ASTM D1525 ³
Thermal Conductivity	0.19	W/m/K	ASTM C177
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (2030 µm)	92.0	%	ASTM D1003
Additional Information	Nominal Value		Test Method
ASTM Classification	PMMA Unspecified		ASTM D788
NOTE			
1.	Annealing cycle: 4hrs @ 176°F		
2.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

