

Hostacom X M2 R13 351236

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom X M2 R13 351236 is a 20% mineral filled elastomer modified polypropylene copolymer. Used for automotive interior trim parts, in particular for instrument panels.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Copolymer		
Uses	Automotive Instrument Panel		
	Automotive Interior Trim		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	5.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	50.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	1700	MPa	ISO 527-2
Tensile Stress (Yield)	20.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	6.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C, Hinged Break	7.0	kJ/m²	
23°C, Hinged Break	15	kJ/m²	
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	55.0	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

