

LG ABS AF365B

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

Description
Flame Retardant, Heat resistant
Application
Electric parts, IT/OA device
TV, monitor housing
Bidet housing

General Information			
UL YellowCard	E67171-100768102		
Features	Good Heat Resistance		
	Flame retardancy		
Uses	Electrical components		
	TV housing		
	Shell		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2060	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	39.2	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield, 3.20mm	5.0	%	ASTM D638
Fracture, 3.20mm	> 20	%	ASTM D638
Flexural Modulus ⁴ (6.40 mm)	2160	MPa	ASTM D790
Flexural Strength ⁵ (6.40 mm)	62.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	88	J/m	ASTM D256
-30°C, 6.40 mm	78	J/m	ASTM D256
23°C, 3.20 mm	290	J/m	ASTM D256

23°C, 6.40 mm	250	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	91.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	84.0	°C	ASTM D648
Vicat Softening Temperature	92.0	°C	ASTM D1525 ⁶
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI	60.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.8 mm	V-1		UL 94
	V-0		
2.0 mm	5VB		UL 94
	V-0		
3.0 mm	5VA		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	170 - 190	°C	
Middle Temperature	180 - 200	°C	
Front Temperature	190 - 210	°C	
Nozzle Temperature	200 - 230	°C	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	40 - 60	°C	
Back Pressure	0.490 - 0.981	MPa	
Screw Speed	30 - 60	rpm	
Injection instructions			
Minimum Moisture Content: 0.01%			
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	15 mm/min		
5.	15 mm/min		
6.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

