

SABIC® LLDPE 726Q

Linear Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® LLDPE 726Q is a butene linear low density polyethylene resin. This grade is typically designed to give blown films a relatively high stiffness for good machinability and a good overall balance of other performance properties, such as puncture resistance, impact strength and heat sealability. This material contains anti block, slip erucamide and processing aid.

Application

Typical applications for SABIC® LLDPE 726Q are shipping sacks, produce bags, can liners and carrier bags. SABIC® LLDPE 726Q has good optical properties when blended with a LDPE (15-85%).

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Additive	Processing aid		
	Erucamide Lubricating Additive (1250 ppm)		
	Anti-caking agent (750 ppm)		
	Antioxidation		
Features	Low density		
	Butene comonomer		
	Rigidity, high		
	smoothness		
	Perforation resistance		
	Anti-caking property		
	Antioxidation		
	Impact resistance, good		
	Machinable		
Uses	Blown Film		
	Lining		
	Bags		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.926	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (Blown Film)	0.10		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	

Tensile Modulus			ISO 527-3
MD: 50 µm, blown film	220	MPa	ISO 527-3
TD: 50 µm, blown film	240	MPa	ISO 527-3
Tensile Stress			ISO 527-3
MD: Yield, 50 µm, blown film	13.0	MPa	ISO 527-3
TD: Yield, 50 µm, blown film	14.0	MPa	ISO 527-3
MD: Broken, 50 µm, blown film	34.0	MPa	ISO 527-3
TD: Broken, 50 µm, blown film	27.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 50 µm, blown film	600	%	ISO 527-3
TD: Broken, 50 µm, blown film	700	%	ISO 527-3
Impact	Nominal Value	Unit	Test Method
Impact Strength - Blown Film (50.0 µm)	230	J/cm	ASTM D4272
Blocking - Blown Film (50.0 µm)	10	g	Internal method
Puncture Resistance - Blown Film (50.0 µm)	440	J/m	Internal method
Re-blocking - Blown Film (50.0 µm)		g	Internal method
Tear Strength ¹			ISO 6383-2
MD : 50.0 µm	23.0	kN/m	ISO 6383-2
TD : 50.0 µm	130.0	kN/m	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	110	°C	ISO 306/A
Melting Temperature (DSC)	124	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 µm, Blown Film)	65		ASTM D2457
Haze (50.0 µm, Blown Film)	14	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Film of 50 µm and BUR=2 has been produced on Kiefel IBC with 130 kg/h. Die size 200 mm, die gap 0.8 mm.			
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT