

IDI SMC S30 (Glass Content 20%)

Thermoset, Unspecified

IDI Composites International

Message:

PRODUCT SERIES: S30 SERIES SMC

PRODUCT DESCRIPTION: LOW PROFILE AUTOMOTIVE GRADE

Low shrink composite materials. Well suited for applications requiring shrink <0.1%.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Low Shrinkage		
Uses	Automotive Applications		
Forms	SMC - Sheet Molding Compound		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.75 to 1.95	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.20 to 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	15 to 60		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12400	MPa	ASTM D638
Tensile Strength	62.1	MPa	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Compressive Strength	186	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	640	J/m	ASTM D256
Unnotched Izod Impact	850	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 204	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Burning Rate	17	mm/min	ASTM D635

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

