

# Cellophane™ 335WSZB

Regenerated Cellulose

Innovia Films Ltd.

## Message:

Vinyl Coated Barrier Films for Packaging Applications  
White 2 side, VC/VA copolymer coated heat sealable, semi-permeable film  
Literature reference: A370

General Information			
Features	Biodegradable		
	Copolymer		
	Heat Sealable		
	Renewable Resource Content		
	Semipermeable		
Uses	Film		
	Packaging		
Appearance	White		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Seal Initiation Temperature <sup>1</sup> (22 µm)	55.0 to 105	°C	
Oxygen Transmission Rate (Wet) (23°C, 22 µm, 0.0% RH)	3.00	cm <sup>3</sup> /m <sup>2</sup> /24 hr	ASTM F1927
Water Vapor Transmission Rate (22 µm, 38°C, 90% RH)	370	g · mm/m <sup>2</sup> /atm/24 hr	ASTM E96
Film Gauge	21.9	µm	Internal Method
Yield (21.9 µm)	29.9	m <sup>2</sup> /kg	Internal Method
NOTE			

1. 0.5 sec dwell, 0.069 MN/m<sup>2</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT