

Amilan® CM1001G-20

Polyamide 6
Toray Resin Company

Message:

Amilan® CM1001G-20 is a Polyamide 6 (Nylon 6) product filled with 20% glass fiber. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
Flame Rated
High Flow

General Information				
UL YellowCard		E41797-233402		
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Features		High Flow		
Part Marking Code		>PA6-GF20<		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.29	--	g/cm ³	ISO 1183
Molding Shrinkage				Internal Method
Across Flow : 3.00 mm ¹	0.60 to 0.90	--	%	
Flow : 3.00 mm ²	0.30 to 0.50	--	%	
Water Absorption				ISO 62
23°C, 24 hr	1.3	--	%	
Saturation, 23°C	7.8	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ISO 2039-2
M-Scale, 23°C	92	--		
R-Scale, 23°C	120	--		
R-Scale, 80°C	12	--		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (23°C)	120	--	MPa	ISO 527-2
Tensile Strain				ISO 527-2
Break, -40°C	2.5	3.0	%	
Break, 23°C	3.0	4.5	%	
Break, 80°C	5.0	5.5	%	
Flexural Modulus				ISO 178
-40°C	8700	7300	MPa	
23°C	6800	3500	MPa	
80°C	3200	2600	MPa	
Flexural Stress				ISO 178
-40°C	275	--	MPa	
23°C	205	--	MPa	
80°C	115	--	MPa	

Compressive Stress				ISO 604
-40°C	240	--	MPa	
23°C	155	80.0	MPa	
80°C	90.0	--	MPa	
Shear Strength (23°C)	115	65.0	MPa	ASTM D732
Taber Abrasion Resistance (1000 Cycles)	0.300	--	mg	ISO 9352
Coefficient of Friction - vs. Metal ³	0.150	--		Suzuki Method
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	6.0	7.0	kJ/m ²	
23°C	7.0	8.5	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-40°C	25	30	kJ/m ²	
23°C	55	70	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)				
	215	--	°C	ISO 75-2/B
Melting Temperature	225	--	°C	DSC
CLTE - Flow	3.0E-5	--	cm/cm/°C	ISO 11359-2
Specific Heat	1600	--	J/kg/°C	
Thermal Conductivity	0.33	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+12	ohms · cm	IEC 60093
Electric Strength	20	--	kV/mm	IEC 60243-1
Dielectric Constant ⁴				IEC 60250
23°C, 50 Hz	4.60	--		
23°C, 1 kHz	4.40	--		
23°C, 1 MHz	3.80	--		
Dissipation Factor ⁵				IEC 60250
23°C, 50 Hz	0.040	--		
23°C, 1 kHz	0.040	--		
23°C, 1 MHz	0.030	--		
Arc Resistance ⁶	120	--	sec	UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.59 mm)	HB	--		UL 94
NOTE				
1.	80x80x3			
2.	80x80x3mm			
3.	Without Lubrication			

4.	60% RH
5.	60% RH
6.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

