

Hostaform® S 9363

Acetal (POM) Copolymer

Celanese Corporation

Message:

Hostaform® acetal copolymer grade S 9363 is an impact modified grade for demanding applications. Hostaform® S 9363 provides good impact strength while improving modulus and weld line strength over standard impact modified grades such as Hostaform® S 9064.

Chemical abbreviation according to ISO 1043-1: POM-HI

General Information			
UL YellowCard	E38860-100674464		
Additive	Impact modifier		
Features	Impact modification		
	Impact resistance, good		
RoHS Compliance	Contact manufacturer		
Resin ID (ISO 1043)	POM-HI		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	5.50	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.6	%	ISO 294-4
Flow direction	1.8	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.80	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	12	%	ISO 527-2/1A/50
Flexural Modulus (23°C)	2000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	148	°C	ISO 75-2/B
1.8 MPa, not annealed	84.0	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3

Linear thermal expansion coefficient			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral	1.1E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	3.0	hr	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	180 - 190	°C	
Nozzle Temperature	180 - 200	°C	
Processing (Melt) Temp	180 - 200	°C	
Mold Temperature	60.0 - 70.0	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			
Zone 4 Temperature: 180 to 200°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

